

## Technical Information

## DABCO® T-9 Catalyst

## Description

DABCO® T-9 catalyst (stannous octoate) is a strong metal based urethane (polyol – isocyanate) catalyst that is primarily used in flexible slabstock polyurethane foams.

## Special properties/Highlights

- Uniform activity
- Excellent stability

## Application

DABCO® T-9 catalyst is recommended for use in flexible slabstock polyether foams. It is also used successfully as a catalyst for polyurethane coatings and sealants.

## Typical physical properties

Flash Point, °C (PMCC)	138
Viscosity at 25 °C, cPs	250
Specific gravity @ 21 °C (g/cm <sup>3</sup> )	1.25
Calculated OH number, mg KOH/g	687
Water solubility	Insoluble
Appearance	Light yellow liquid

## Recommended storage conditions

DABCO® T-9 catalyst has a shelf life of 24 months from the date of manufacture and under the condition, that it is stored in factory-packed containers and protected against extreme weather conditions, particularly against heat and moisture. The optimum storage temperature of DABCO® TMR-9 catalyst is in between 10°C and 30°C. Lower and higher storage temperatures are not preferable and should be avoided.

## Information concerning

- classification and labelling according to regulations for transport of chemicals
- protective measures for storage and handling
- measures in case of accidents and fires
- toxicological and ecotoxicological effects

is given in our safety data sheets.

## Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

## Evonik Nutrition &amp; Care GmbH

Goldschmidtstraße 100  
45127 Essen, Germany  
Phone: 49 201 173-2464  
Fax: 49 201 173-1991

[polyurethane@evonik.com](mailto:polyurethane@evonik.com)  
[www.evonik.com/polyurethane-additives](http://www.evonik.com/polyurethane-additives)

## For Technical Information, Support and Samples:

Americas: [picias@evonik.com](mailto:picias@evonik.com)  
Asia: [piciasia@evonik.com](mailto:piciasia@evonik.com)  
EMEA: [apcse@evonik.com](mailto:apcse@evonik.com)